



Technical specifications

Onyx impact meets the requirements of EN 15102 and EN 233

	Total thickness	EN ISO 24346	1,50 mm
	Thickness wear layer	EN ISO 24340	0,10 mm
	Surface finish		PUR
	Collection size		6
	Roll width	EN ISO 24341	2,0 m
	Roll length	EN ISO 24341	21 m
	Total weight	EN ISO 23997	2500 g/m ²
	Dimensional stability	EN ISO 23999	≤ 0,4 %
	Light fastness	ISO 105-B02	≥ 6
	Resistance to chemicals	EN ISO 26987	good
	Impact resistance	EN 235	resistant to impact
	Indoor Air Emissions: TVOC after 28 days	ISO 16000-6	≤ 0,01 mg/m ³
	Bacteria and fungi resistance	ISO 846	does not favour growth
	Cleanroom particle emission	ISO 14644-1	ISO 3
	Washability	EN 233	washable and scrubbable
	Recycled content		≥ 20%
	<small>EN 15101</small> <small>0900721-04P-210</small>		
	Onyx impact meets the requirements of EN 15102		
	Reaction to fire	EN 13501-1	B-s2,d0