


Technical specifications

Marmoleum sheet meets the requirements of EN-ISO 24011

COMMITTED TO THE HEALTH OF ONE
WWW.FORBO-FLOORING.COM/CHO



	Marmoleum sheet Striato original & colour	Marmoleum Striato textura
Total thickness	EN-ISO 24346	2.5 mm
Surface finish		
Domestic use	EN-ISO 10874	Class 23, heavy
Commercial use	EN-ISO 10874	Class 34, very heavy
Light Industrial use	EN-ISO 10874	Class 43, heavy
Roll width	EN-ISO 24341	2.00 m
Roll length	EN-ISO 24341	≤ 33 m
Residual indentation <i>Typical value</i>	EN-ISO 24343-1	≤ 0.15 mm ~0.08 mm
Castor chair continuous use	ISO 4918/ EN 425	Suitable for office chairs with castors
Light fastness	EN-ISO 105-B02	Method: 3 blue scale > 6
Flexibility	EN-ISO 24344	ø 40 mm
Resistance to chemicals	EN-ISO 26987	Resistant to diluted acids, oils, fats and to the conventional solvents. Not resistant to prolonged exposure to alkalis.
Bacteriostatic properties*	Marmoleum has natural bacteriostatic properties which are confirmed by independent laboratories, even against the bacteria MRSA.	
Cigarette resistance	EN 1399	There is no melting of the surface by cigarettes. Marks left on Marmoleum as a result of stubbed-out cigarettes can be removed.
Acoustical impact sound reduction	EN-ISO 717-2	≤5 dB
Indoor Air Emissions: TVOC at 28 days	EN ISO 16000-9	< 50 µg/m ³
Life Cycle Assessment**	LCA is the foundation for securing the lowest environmental impact.	
Creating better environments		
CO₂	Marmoleum is produced CO ₂ neutral.	
renewable electricity	Marmoleum is manufactured using 100% electricity from renewable sources.	
	Marmoleum is made of 94-98% natural materials.	
	Marmoleum contains PEFC certified wood flour.	
	Marmoleum is free of PVC, PET, synthetic rubber and plasticizers.	
	Marmoleum is REACH compliant.	
recycled content	Marmoleum contains recycled content.	
Application on underfloor heating	yes	

Marmoleum meet the requirements of EN 14041



Product code	EN 14041	0100201-DoP-306	
Reaction to fire	ISO 9239-1	>8kW/m ² <750% min	
Slip resistance	AS 4586	R10 - P2	
Body voltage	EN 1815	≤ 2 kV	≤ 2 kV
Thermal conductivity	EN 12524	0.17 W/m-K	0.17 W/m-K

* Marmoleum sheet can be installed nett fit, or with a welding rod in the seam. Both are proven hygienic solutions.
** Application of Marmoleum sheet can help maximize contribution in the project/building for LEED qualification
Our recommended adhesive for Marmoleum is 414 Forbo Fix.

All Forbo Flooring Systems' sales organisations worldwide have a certified Quality Management System in accordance with ISO 9001.
All Forbo Flooring Systems' manufacturing operations have a certified Environmental Management System in accordance with ISO 14001.
The Life Cycle Assessment (LCA) of Forbo Flooring Systems' products is documented in individual Environmental Product Declarations (EPD's) which can be found on all of our websites.



DOWNLOADS:

- Marmoleum digital magazine
- Marmoleum VOC test report
- Marmoleum | slip report | AS 4586
- Marmoleum FAQ
- Marmoleum | fire report | AS 9239-1
- 10 Year Commercial Warranty form
- Marmoleum | fire report (walls) AS 3837